

A novel high-spin heterometallic Ni₁₂K₄ cluster incorporating large Ni–azide circles and an *in situ* cyanomethylated di-2-pyridyl ketone†

Ming-Liang Tong,^{*a} Montserrat Monfort,^b Juan Modesto Clemente Juan,^c Xiao-Ming Chen,^a Xian-He Bu,^d Masaaki Ohba^d and Susumu Kitagawa^{*d}

Received (in Cambridge, UK) 5th October 2004, Accepted 26th October 2004

First published as an Advance Article on the web 26th November 2004

DOI: 10.1039/b415431b

Reaction of di-2-pyridyl ketone (dpk) with nickel acetate and azide in the presence of potassium *tert*-butylate as a catalytic base generates the title compound, which contains the largest [Ni(μ_{1,1}-N₃)₆] circles in the discrete ferromagnetically-coupled M^{II}-azide cluster family, and shows an unprecedented *in situ* cyanomethylation of ketone.

The synthesis of new magnetic metal circles with high-spin topologies is one of the central topics in the field of molecular magnetism. Several transition metals and bridging ligands have been employed in the synthesis of a variety of metallacyclic rings, such as the intriguing decanuclear “ferric wheels” of formula [Fe(OMe)₂(L)]₁₀^{1a} pioneered by Lippard and co-workers and [cis-Cu^{II}(μ-OH)(μ-pz)]_n rings (*n* = 6, 8, 9, 12, and 14).^{1b} Of strongly ferromagnetic superexchange bridges, the azide ligand is the most versatile at bridging metal ions. A number of polynuclear and polymeric magnetic complexes with azido bridging ligands have been reported to date.^{2,3} It is clear that the N₃[−] anion acts as a bridging ligand in two typical coordination modes, end-on (EO or 1,1) and end-to-end (EE or 1,3). The end-to-end (EE) coordination mode usually exhibits antiferromagnetic coupling, the end-on (EO) exhibits ferromagnetic coupling, and the magnetic coupling may be reversed for very large M–(μ_{1,1}-N₃)–M bond angles.⁴ However, it is still a challenge for the discrete M^{II}-azido magnetic cluster system to assemble large metal circles bridged by the ferromagnetically-coupled μ_{1,1}-azido ligands. To our knowledge, such systems remain extremely rare thus far. Working towards this goal, we did successfully furnish such an interesting magnetic cluster system, {K[C[Ni₆(μ₆-CO₃)(μ_{1,1}-N₃)₆(μ-OAc)₃-(dpkMeCN-H)₃]}₂[K₂(H₂O)₂]·3MeCN·7H₂O (1·3MeCN·7H₂O), which is composed of two large [Ni(μ_{1,1}-N₃)₆] circles joined by a K₂(H₂O)₂ unit forming a new sandwich-type high-spin heterometallic Ni₁₂K₄ cluster, and an unprecedented polydentate ligand generated *in situ* (Fig. 1a) as a result of the cyanomethylation of ketone was also obtained.

Reaction of Ni(OAc)₂ with di-2-pyridyl ketone (dpk), sodium azide, and potassium *tert*-butylate (*t*-BuOK) (1 : 0.5 : 1 : 2 molar ratio) in acetonitrile at room temperature led to a pale green solution from which the block deep green crystals of 1·3MeCN·7H₂O were isolated.‡

† Electronic supplementary information (ESI) available: synthesis and X-ray crystallography, figures, ac magnetic susceptibilities and field dependence of 1. See <http://www.rsc.org/suppdata/cc/b4/b415431b/> *cestml@zsu.edu.cn (Ming-Liang Tong) kitagawa@sbchem.kyoto-u.ac.jp (Susumu Kitagawa)

One of the most intriguing features regarding the synthesis is the direct structural observation of the C–H bond activation of the acetonitrile; a product of the α-alkylation of acetonitrile, dpkMeCN, was generated *in situ* by the reaction of acetonitrile and di-2-pyridyl ketone under the mild conditions of ambient temperature and the presence of air. It should be noted that another tetranuclear cluster, [Ni₄(dpk-H)₄(N₃)₂(OAc)₂]·2MeCN (dpk-H = (2-py)C(OH)(O)[−]),⁵ was obtained if such a reaction was carried out without potassium *tert*-butylate, suggesting that the presence of potassium *tert*-butylate is the key to performing such a ligand reaction. The same product as 1 was prepared under the same reaction conditions except for the use of anhydrous Ni(OAc)₂ instead of Ni(OAc)₂·4H₂O. The acetonitrile and dpk in the synthesis of 1 prefer undergoing an unprecedented reaction (Scheme S1†), different from previously reported phenomena.^{6–8} Moreover, our synthetic route to β-hydroxy nitriles suggests that it may be potentially useful for the addition of nitrile anions to




Fig. 1 Schematic presentation of the dpkMeCN ligand generated *in situ* (a), and perspective views of the local coordination geometries (b) and sandwich-type heterometallic Ni₁₂K₄ cluster (c) in the structure of 1.

aldehydes (or ketones), which yield an important group of synthetic organic intermediates.

The crystal structure of **1** comprises Ni_{12}K_4 clusters and disordered solvated water and acetonitrile molecules. The Ni_{12}K_4 cluster is located on a crystallographic inversion centre. There are six crystallographically unique (but chemically similar) Ni atoms, two unique K atoms, one carbonate, three unique dpkMeCN–H ligands, six unique N_3^- ions, three unique acetates and one aqua ligand in the structure of **1** (Fig. 1b,c). The six Ni atoms are bridged by six $\mu_{1,1}\text{-N}_3$ groups (three up and three down the circle plane) to form a $[\text{Ni}(\text{N}_3)_6]$ circle ($\text{Ni}\cdots\text{Ni} = 2.960\text{--}3.145 \text{ \AA}$), and the three mono-oxygen bridges from three dpkMeCN–H ligands and three μ -acetate bridges are alternately mounted between the six Ni atoms. The six pyridyl N atoms from three dpkMeCN–H ligands coordinate to the six Ni atoms from the outside of the $[\text{Ni}(\text{N}_3)_6]$ circle. The three acetate groups are oriented downwards from the circle and the three cyanomethyl groups of the three dpkMeCN–H ligands are oriented upwards, resulting in a cage. The K atom is located in this cage and interacts with the surrounding O atoms from the dpkMeCN–H ligands ($2.836(6)\text{--}3.141(7) \text{ \AA}$), the N atoms from the azide groups and cyano groups ($2.964(13)\text{--}3.149(13) \text{ \AA}$) and the C atoms from the cyano groups ($3.135(13)\text{--}3.155(12) \text{ \AA}$). It is interesting to note that one carbonate is located at the center of the $[\text{Ni}(\text{N}_3)_6]$ circle coordinated to the six Ni atoms in a less common μ_6 hexadentate fashion.⁹ Therefore, each Ni is coordinated to three N atoms (two from two *trans*-azides with $\text{Ni}\text{--}\text{N} = 2.070(8)\text{--}2.122(8) \text{ \AA}$ and one from a pyridyl with $\text{Ni}\text{--}\text{N} = 2.042(8)\text{--}2.072(9) \text{ \AA}$) and three O atoms separately from one acetate ($\text{Ni}\text{--}\text{O} = 2.006(7)\text{--}2.058(7) \text{ \AA}$), one dpkMeCN–H ($\text{Ni}\text{--}\text{O} = 2.048(7)\text{--}2.065(7) \text{ \AA}$) and one carbonate ($\text{Ni}\text{--}\text{O} = 2.086(6)\text{--}2.181(6) \text{ \AA}$). It is noteworthy that the six-membered $[\text{Ni}(\mu_{1,1}\text{-N}_3)_6]$ circle in **1** is the largest metal circle bridged by ferromagnetically-coupled $\mu_{1,1}$ -azide ligands present in M–azide magnetic cluster systems to date. Another example is the $[\text{Ni}(\mu_{1,1}\text{-N}_3)_4]$ circle found in $[\text{Ni}_4(2\text{-oxo-1,3-diaminopropane})_2(2\text{-hydroxo-2,3-diaminopropane})_2(\mu_{1,1}\text{-N}_3)_4](\text{ClO}_4)_2$.¹⁰ The whole structure of **1** is a heterometallic Ni_{12}K_4 cluster. The centrosymmetrically related $\text{K}_2(\text{H}_2\text{O})_2$ unit is situated between two $[\text{Ni}(\mu_{1,1}\text{-N}_3)_6]$ circles and makes close contact with the acetate

and azide groups ($\text{K}\text{--}\text{O} = 2.748(9)\text{--}3.164(9)$; $\text{K}\text{--}\text{N} = 2.837(9)\text{--}3.004(9) \text{ \AA}$), resulting in a sandwich-type cluster.

The magnetic behaviour between 2 and 300 K was investigated (Fig. 2). The $\chi_{\text{M}}T$ curve increases continuously upon cooling from 300 K to 4.5 K, after which $\chi_{\text{M}}T$ rapidly decreases. This pattern is compatible with moderate ferromagnetic coupling; the sudden decrease in $\chi_{\text{M}}T$ is associated with the anisotropy of the Ni(II) ions. The field magnetization data in the range 0–5 T were checked at 2 K (Fig. S2†). The value of the magnetization at 5 T ($12.4 N\beta$) is smaller than expected for an $S = 6$ state (13.6 for $g = 2.28$). The in-phase (χ'_{M}) and out-of-phase magnetic susceptibility (χ''_{M}) signals (Fig. S3†) were checked. No out-of-phase ac signal and no hysteresis loop indicate that **1** does not behave as a SMM.

A full analysis of the magnetic exchange interactions has been performed by means of the full-matrix diagonalization program MAGPACK,¹¹ applying the Hamiltonian, $H = -\sum J_{ij}S_iS_j + \sum D_iS_i^2$, the exchange pathway connecting the Ni(II) ions can be schematized as shown in Fig. 2. The best-fit parameters obtained with this computing model are: $J_1 = 2.88 \text{ cm}^{-1}$, $J_2 = 25.4 \text{ cm}^{-1}$, $D = 10.3 \text{ cm}^{-1}$ and $g = 2.28$ (J_3 and J_4 were fixed to 0).

All values of the J and D parameters seem to be consistent, taking into account the symmetry and the geometry of Ni(II) ions. J_1 and J_2 relate the peripheral neighboring spins in alternate form. The net superexchange coupling value found corresponds to the combined interactions due to the end-on azido bridges for both J_1 and J_2 , an oxo group supplied from the ligand in J_1 and from carbonate in J_2 and a carboxylate group in *syn-syn* mode (carbonate in J_1 and acetate in J_2). For the EO azido bridge in Ni(II) complexes, the interaction is predicted to be ferromagnetic, with J increasing upon increasing the angle, yielding a maximum at 104° .⁴ In the present compound, the $\text{Ni}\text{--}\text{N}_{\text{azido}}\text{--}\text{Ni}$ angle between the Ni(II) ions related by J_1 is smaller than that related by J_2 . The $\text{Ni}\text{--}\text{O}\text{--}\text{Ni}$ angles are in the range for $\text{Ni}\cdots\text{Ni}$ ferromagnetic exchange pathways to be dominant ($90 \pm 14^\circ$).¹² Weak antiferromagnetic interactions are observed in the carboxylate-bridged nickel(II) in *syn-syn* mode.¹³ This contribution diminishes the ferromagnetic exchange in both J_1 and J_2 . It is well demonstrated that in the compounds where azido and acetato bridges simultaneously coexist, the effect of the countercomplementarity is found and enhances the ferromagnetic interaction.¹⁴ Then the large value for the $\text{Ni}\text{--}\text{N}_{\text{azido}}\text{--}\text{Ni}$ angle present in the $\text{Ni}\cdots\text{Ni}$ pathway related by J_2 and the effect of the countercomplementarity mentioned just about justifies the greater value for J_2 than for J_1 .

Syn-anti and *anti-anti* coordination modes for carbonate magnetically allow weak ferro or antiferromagnetic coupling. Due to very small values found (less than $\pm 0.1 \text{ cm}^{-1}$) for J_3 and J_4 and the over-parametrization, it is impossible to determine properly their values and they were fixed to zero in the best fit.

The sign of the D parameter in the best fit is positive and attempts to fit the susceptibility data with negatives values of D failed. A value of $D > 0$ is in agreement with the absence of SMM properties.

This work was supported by the FANEDD of PR China, the NSFC and EYTP of MOE P. R. China, the Spanish Government (Grant BQU2003/00539 and BQU2002-01091), and the Grant-in-Aid for JSPS Fellows.




Fig. 2 Plot of $\chi_{\text{M}}T$ vs. T . Solid line represents the best fit with the parameters given in the text (inset: the exchange pathway connecting the Ni(II) ions).

Ming-Liang Tong,^{*a} Montserrat Monfort,^b
Juan Modesto Clemente Juan,^c Xiao-Ming Chen,^a Xian-He Bu,^d
Masaaki Ohba^d and Susumu Kitagawa^{*d}

^aSchool of Chemistry and Chemical Engineering, Sun Yat-Sen University, Guangzhou 510275, China. E-mail: cestml@zsu.edu.cn; Fax: +86 20 8411-2245

^bDepartament de Química Inorgànica, Universitat de Barcelona, Martí i Franquès 1-11, 08028-Barcelona, Spain

^cInstituto de Ciencia Molecular, Universidad de Valencia, C/ Dr. Moliner 50, E-46100 Burjassot, Spain

^dDepartment of Synthetic Chemistry and Biological Chemistry, Graduate School of Engineering, Kyoto University, Katsura, Nishikyoku, Kyoto 615-8510, Japan. E-mail: kitagawa@sbchem.kyoto-u.ac.jp

Notes and references

‡ CCDC 238449. See <http://www.rsc.org/suppdata/cc/b4/b415431b/> for crystallographic data in .cif or other electronic format.

- (a) K. L. Taft, C. D. Delfs, G. C. Papaefthymiou, S. Foner, D. Gatteschi and S. J. Lippard, *J. Am. Chem. Soc.*, 1994, **114**, 823; (b) G. Mezei, P. Baran and R. G. Raptis, *Angew. Chem., Int. Ed.*, 2004, **43**, 574.
- J. Ribas, A. Escuer, M. Monfort, R. Vicente, R. Cortés, L. Lezama and T. Rojo, *Coord. Chem. Rev.*, 1999, **193–195**, 1027; L. K. Thompson, *Coord. Chem. Rev.*, 2002, **233**, 193.
- E.-Q. Gao, S.-Q. Bai, Z.-M. Wang and C.-H. Yan, *J. Am. Chem. Soc.*, 2003, **125**, 4984; T.-F. Liu, D. Fu, S. Gao, Y.-Z. Zhang, H.-L. Sun, G. Su and Y.-J. Li, *J. Am. Chem. Soc.*, 2003, **125**, 13976.
- E. Ruiz, J. Cano, S. Alvarez and P. Alemany, *J. Am. Chem. Soc.*, 1998, **120**, 11122.
- M.-L. Tong, unpublished work.
- E. C. Constable, *Metals and Ligand Reactivity*, VCH, Weinheim, 1996, pp. 57–58.
- A. K. Boudalis, B. Donnadieu, V. Nastopoulos, J. M. Clemente-Juan, A. Mari, Y. Sanakis, J.-P. Tuchagues and S. P. Perlepes, *Angew. Chem., Int. Ed.*, 2004, **43**, 2266; M.-L. Tong, S.-L. Zheng, J.-X. Shi, Y.-X. Tong, H. K. Lee and X.-M. Chen, *J. Chem. Soc., Dalton Trans.*, 2002, 1727; M. G. Barandika, Z. Serna, R. Cortes, L. Lezama, M. K. Urriaga, M. I. Arriortua and T. Rojo, *Chem. Commun.*, 2001, 45 and the references cited therein.
- R. A. Michelin, M. Mozzon and R. Bertani, *Coord. Chem. Rev.*, 1996, **147**, 299.
- M. J. Manos, A. D. Keramidas, J. D. Woollins, A. M. Z. Slawin and T. A. Kabanos, *J. Chem. Soc., Dalton Trans.*, 2001, 3419.
- J. Ribas, M. Monfort, R. Costa and X. Solans, *Inorg. Chem.*, 1993, **32**, 695.
- J. J. Borrás-Almenar, J. M. Clemente-Juan, E. Coronado and B. Tsukerblat, *Inorg. Chem.*, 1999, **38**, 6081; J. J. Borrás-Almenar, J. M. Clemente-Juan, E. Coronado and B. Tsukerblat, *J. Comput. Chem.*, 2001, **22**, 985.
- K. K. Nanda, L. K. Thompson, J. N. Bridson and K. Nag, *J. Chem. Soc., Chem. Commun.*, 1994, 1337 and references therein.
- S. Husebye, M. Kato, K. Maartman-Moe, Y. Muto, M. Nakashima and T. Tokii, *Acta Chem. Scand.*, 1994, **48**, 628.
- A. Escuer, R. Vicente, F. A. Mautner and M. A. S. Goher, *Inorg. Chem.*, 1997, **36**, 1233.