Thermal- and photo-induced spin crossover in the 1D coordination polymer $[\text{Fe}(\text{4-}t\text{Bupy})_3][\text{Au}(\text{CN})_2]_2$ (4-*t*Bupy = 4-*tert*-butylpyridine)

Víctor García-López, Miguel Clemente-León,^{a)} and Eugenio Coronado

AFFILIATIONS

Instituto de Ciencia Molecular (ICMol), Universidad de Valencia, Catedrático José Beltrán 2 46980, Paterna, Spain

Note: This paper is part of the Special Topic on Spin Transition Materials: Molecular and Solid-State.

^{a)}Author to whom correspondence should be addressed: miguel.clemente@uv.es

ABSTRACT

Reaction of the unidentate pyridine ligand containing a bulky *t*-butyl substituent with Fe^{2+} and $[\text{Au}(\text{CN})_2]^-$ affords a new type of spin crossover (SCO) coordination polymer in the 1D compound $[\text{Fe}(\text{4-}t\text{Bupy})_3][\text{Au}(\text{CN})_2]_2 \cdot 0.5\text{H}_2\text{O}$ (**1**), which is formed by chains of Fe(II) complexes linked through bridging $[\text{Au}(\text{CN})_2]^-$ with three terminal 4-*t*Bupy and one monodentate $[\text{Au}(\text{CN})_2]^-$ ligands completing the octahedral coordination around Fe(II). Longer reaction times led to the minor products $[\text{Fe}(\text{4-}t\text{Bupy})_2][\text{Au}(\text{CN})_2]_2$ (**2**), which presents a 2D structure more similar to that found in the other SCO compounds based on $[\text{Au}(\text{CN})_2]^-$, and the 1D compound $[\text{Fe}(\text{4-}t\text{Bupy})_2(\text{MeOH})][\text{Au}(\text{CN})_2]_2$ (**3**), in which one of the three terminal 4-*t*Bupy found in **1** is replaced by a coordinating MeOH molecule. Magnetic measurements of **1** show an abrupt spin transition with the temperature with hysteresis and light-induced excited spin-state trapping effect. Structural analysis of **2** and **3** indicates that Fe(II) remains in the high-spin state in these compounds.

I. INTRODUCTION

Spin crossover (SCO) compounds can be switched in a reversible way between two distinct states by different external stimuli such as light, temperature, pressure, electric field, or analytes.¹ Since this phenomenon induces reversible changes of a number of physical properties, SCO materials are promising candidates for many applications such as sensors, memories, or as part of spintronic devices.^{2–4} Fe(II) complexes, which undergo SCO between the diamagnetic low-spin state (LS, $S = 0$) and the paramagnetic high-spin state (HS, $S = 2$), are the most studied ones.

A remarkable family of SCO Fe(II) compounds are Hofmann-like coordination polymers of formula $[\text{Fe}^{\text{II}}(\text{L})_x\text{M}(\text{CN})_y]$. They are constructed, in most cases, by the equatorial coordination of tetracyano- $[\text{M}^{\text{I}}(\text{CN})_4]^{2-}$ with $\text{M} = \text{Pt}, \text{Pd}$ or Ni) or dicyano- $[\text{M}^{\text{I}}(\text{CN})_2]^-$ with $\text{M} = \text{Ag}$ or Au) metallates and the axial coordination of aromatic N-donor ligands (L), where L can be unidentate or bidentate bridging ligands to build 2D or 3D coordination networks, respectively. This family of compounds exhibits very attractive SCO properties. Thus, they present cooperative SCO thanks to

an effective propagation throughout the lattice architecture, which is induced primarily via their short and flexible metallo-cyanide bridges. Interestingly, these interactions can be modulated thanks to a rich host-guest chemistry in many examples of Hofmann-like porous compounds, which show in some cases multi-step transitions associated with symmetric breaking or solvent disorder.⁵ Additional advantages of these systems are the possibility to be miniaturized as thin films or nanoparticles, which provides processability at the nanoscale level,⁶ and their chemical versatility. In this sense, multifunctional SCO compounds have been obtained by replacing the axial ligand or adding functional guest molecules.⁷

Hofmann-like SCO compounds derived from dicyanometalates have received less attention than those constituted of tetracyanometalates, because the higher connectivity generated by the bridging square planar anions, $[\text{M}^{\text{I}}(\text{CN})_4]^{2-}$, usually leads to more dense and robust frameworks with stronger cooperative behavior.⁸ Furthermore, the open frameworks generated by dicyanometalate linkers favor interpenetration and decrease the effective size of the pores.⁹ Most of the examples of $[\text{Fe}(\text{L})_2][\text{M}^{\text{I}}(\text{CN})_2]_2$ ($\text{M} = \text{Ag}$ or Au) compounds contain 2D frameworks constructed from the

equatorial coordination of four dicyanometallate linkers to Fe(II) and small unidentate axial ligands such as 3-Xpyridine with X = F, Cl, Br, or I,¹⁰ 3-cyanopyridine,¹¹ pyrimidine,¹² 4-methylpyridine,¹³ or 4-methylpyrimidine,¹⁴ which have been systematically studied. However, there are very few examples on the use of pyridine derivatives bearing bulky substituents (L = 4-phenylpyridine,¹⁵ 4'-dimethylaminostilbazole, and 4'-diethylaminostilbazole).¹⁶ We have explored this last possibility in the search of new structures with a better isolation between the 2D layers, which could be useful for exfoliation and incorporation on devices, and to avoid interpenetration. We have then tempted in this work the use of the unidentate pyridine ligand with a bulky substituent, 4-*tert*-butylpyridine (4-*t*Bupy). This has led to a new structure with an unusual coordination of Fe(II) displaying an abrupt thermal SCO with temperature and light-induced excited spin-state trapping (LIESST) effect. To our knowledge, there is only one report using this ligand for the preparation of Hofmann-like structures combined with [Ni(CN)₄]²⁻, which is not focused on the SCO properties of the material.¹⁷

II. EXPERIMENTAL SECTION

Synthesis of [Fe(4-*t*Bupy)₃][Au(CN)₂]₂·0.5H₂O (**1**), [Fe(4-*t*Bupy)₂][Au(CN)₂]₂ (**2**), and [Fe(4-*t*Bupy)₂(MeOH)][Au(CN)₂]₂ (**3**): A solution of Fe(SO₄)₂(NH₄)₂·6H₂O (78.42 mg, 0.1 mmol) and 4-*t*Bupy (30 mg, 0.1 mmol) in a 2:1 mixture of water/methanol (3 ml) was layered on top of 3 ml an aqueous solution of K[Au(CN)₂] (112 mg, 0.2 mmol). After a few days, colorless needles of **1** suitable for x-ray diffraction were obtained in the top of the diffusion tube (26.5 mg, yield ~80%). If the slow diffusions were left for longer times, colourless prismatic crystals of **2** were obtained in the middle of the diffusion tubes. In one of the syntheses, a few needles of **3** were found on top of the diffusion tubes together with those of **1**. The composition of the crystals, checked by microanalysis, shows an Fe:Au ratio close to 1:2. Anal. Calcd for **1** FeAu₂N₇C₃₁H₄₀O_{0.5}: 38.44; H, 4.15; N, 10.12%. Found: C, 38.81; H, 4.10; N, 10.22%.

Single crystals of **1**, **2**, and **3** were mounted on a glass fiber using a viscous hydrocarbon oil to coat the crystal and then transferred directly to the cold nitrogen stream for data collection at 120, 175, and 225 K (**1**), 120 K (**2**), and 150 K (**3**) on a Supernova diffractometer equipped with a graphite-monochromated Enhance (Mo) x-ray Source ($\lambda = 0.71073$ Å). The program CrysalisPro, Oxford Diffraction Ltd., was used for unit cell determinations and data reduction. Empirical absorption correction was performed using spherical harmonics, implemented in the SCALE3 ABSPACK scaling algorithm. The structures were solved with the ShelXT structure solution program¹⁸ and refined with the SHELXL-2013 program,¹⁹ using Olex2.²⁰ Non-hydrogen atoms were refined anisotropically, and hydrogen atoms were placed in calculated positions refined using idealized geometries (riding model) and assigned fixed isotropic displacement parameters. Crystallographic data are summarized in Tables S1 and S2 in the [supplementary material](#). CCDC-2059587–2059591 contain the supplementary crystallographic data for this paper. These data can be obtained free of charge from The Cambridge Crystallographic Data Centre via www.ccdc.cam.ac.uk/data_request/cif. X-ray powder measurements of **1** were performed on an Empyrean PANalytical powder diffractometer, using CuK α radiation ($\lambda = 1.54177$ Å) and 0.5 mm glass

capillaries. A total of 2 scans were collected at room temperature in the 2θ range of 5°–40°.

The Fe/Au ratios were measured with a Philips ESEM X230 scanning electron microscope equipped with an EDAX DX-4 microsonde. Elemental analyses (C, H, and N) were performed with a CE Instruments EA 1110 CHNS Elemental analyzer. Differential scanning calorimetry (DSC) measurements under nitrogen atmosphere were performed in a Mettler Toledo DSC 821e with warming and cooling rates of 10 K min⁻¹.²¹

Magnetic measurements were performed with a Quantum Design MPMS-XL-5 SQUID magnetometer from 2 to 300 K with an applied magnetic field of 0.1 T at a scan rate of 2 K/min (0.3 K/min for photomagnetic measurements). A Diode Pumped Solid State Laser DPSS-532-20 from Chylas (green light, $\lambda = 532$ nm, optical power 3.4 mW cm⁻²) coupled via an optical fiber to the cavity of the SQUID magnetometer was used for photomagnetic measurements.²¹

III. RESULTS AND DISCUSSION

A. Synthesis

[Fe(4-*t*Bupy)₃][Au(CN)₂]₂·0.5H₂O (**1**), [Fe(4-*t*Bupy)₂][Au(CN)₂]₂ (**2**), and [Fe(4-*t*Bupy)₂(MeOH)][Au(CN)₂]₂ (**3**) were synthesized by slow diffusion of a equimolar mixture of Fe²⁺ and 4-*t*Bupy in water/methanol on top of K[Au(CN)₂] in water. After a few days, crystals of **1** suitable for single crystal x-ray diffraction were obtained. A few crystals of the secondary phases **2** and **3** were obtained if the diffusion tubes were left for longer times. Unfortunately, they could not be obtained in sufficient amount to enable a complete characterization. Single crystals of other phases were not found.

The structures of the three compounds were successfully determined by single-crystal x-ray diffraction at low temperatures (see below). The powder x-ray diffraction (PXRD) pattern of **1** at room temperature is consistent with the simulated from the single-crystal x-ray diffraction structure. The purity of **1** was confirmed by elemental analysis (see Sec. II).

B. Structure

The crystal structure of **1** was investigated at three representative temperatures upon heating (120, 175, and 225 K). At all of them, it crystallizes in the monoclinic $P2_1/c$ space group. The asymmetric unit contains one formula unit with two disordered water molecules with occupancies of 0.25 in agreement with elemental analysis. Fe(II) present a FeN₆ octahedral coordination sphere with three N from unidentate 4-*t*Bupy ligands and the remaining three from [Au(CN)₂]⁻ species. Two of the three [Au(CN)₂]⁻ in trans act as bridging ligands and are coordinated to two Fe(II) ions through their two N atoms. This leads to [Fe{Au(CN)₂}]⁻ chains running along the *b* axis [see Fig. 1(a)]. The third [Au(CN)₂]⁻, in trans to a 4-*t*Bupy ligand, acts as a unidentate ligand with only one coordinated N atom. Finally, the Au from bridging [Au(CN)₂]⁻ belonging to a chain and the terminal [Au(CN)₂]⁻ from the neighboring chain are linked through aurophilic interactions (Au—Au = 3.196 Å at 120 K, Au—Au = 3.210 Å at 175 K and Au—Au = 3.224 Å at 225 K) leading to double chains [see Fig. 1(b)]. At 120 and 225 K, these double chains are linked through intermolecular interactions

FIG. 1. (a) Structure of the chains of **1**. (b) Double chains of **1** linked through aurophilic interactions (red-dashed lines). Fe (brown), Au (yellow), C (black), N (blue). Hydrogen atoms and one of the two possible configurations of disordered methyl groups have been omitted for clarity.

that involve CH—CH contacts between *t*-butyl groups, CH— π and CH—CH contacts between *t*-butyl groups and pyridine and a short contact between terminal N atom from unidentate $[\text{Au}(\text{CN})_2]^-$ and CH group from pyridine. At 175 K, CH—CH contacts between *t*-butyl groups are not detected. Two of the three crystallographically independent 4-*t*Bupy ligands present a disorder of the methyl groups at 120 and 225 K, which was modeled with two possible configurations. At 175 K, only one of the three 4-*t*Bupy ligands present this disorder. Fe—N bond lengths range from 2.130(9) to 2.226(9) Å at 225 K, in agreement with a HS

state, and from 1.930(10) to 2.071(10) Å at 120 K, in agreement with a LS state. This is consistent with the complete thermal SCO observed from magnetic measurements in the same range of temperatures (see below). Finally, Fe—N bond lengths at 175 K in the heating mode range from 2.096(8) to 2.205(7) Å. This suggests an intermediate spin state.

This structure displays two original features compared to other coordination polymers based on Fe(II), pyridine derivatives and $[\text{Au}(\text{CN})_2]^-$: (i) There are very few reports of the $\text{Fe}^{\text{II}}(\text{py})_3(\text{N}=\text{C})_3$ coordination sphere as that of **1** with only one of them, reported very

FIG. 2. Projection of the structure of **2** in the *bc* plane. Aurophilic interactions are represented as red-dashed lines. Fe (brown), Au (yellow), C (black), N (blue). Hydrogen atoms have been omitted for clarity.

recently, displaying a SCO behavior and.²² (ii) The coexistence of bridging and unidentate $[\text{Au}(\text{CN})_2]^-$ with terminal CN is unusual with very few examples.²³

The crystal structure of **2** was solved at 120 K. It crystallizes in the triclinic space group *P*-1. The asymmetric unit is constituted by two iron atoms (one of them with an occupancy of 0.5), three 4-*t*Bupy ligands and three bridging $[\text{Au}(\text{CN})_2]^-$ species. Each iron atom is octahedrally coordinated to six nitrogen atoms with the axial positions occupied by two 4-*t*Bupy ligands and the equatorial ones by four $[\text{Au}(\text{CN})_2]^-$. This leads to 2D $[\text{Fe}\{\text{Au}(\text{CN})_2\}_2]_n$ layers in the *[011]* plane, which, in contrast to other 2D compounds of this type, presents a more complicated structure (Fig. 2).^{10–16} Thus, Fe atoms with 0.5 occupancies (Fe2) are placed in the same plane, while Fe atoms with an occupancy of 1 (Fe1) are placed alternatively above and below that plane. This gives rise to a double layer, in which Fe1 and Fe2 are linked through $[\text{Au}(\text{CN})_2]^-$ moieties. Furthermore, two of the three $[\text{Au}(\text{CN})_2]^-$ are linked through aurophilic interactions ($\text{Au}-\text{Au} = 3.251 \text{ \AA}$). Finally, Fe–N bond lengths for Fe1 and Fe2 range from 2.143(3) to 2.227(3) $\text{\AA}$ and 2.155(4) to 2.193(4) $\text{\AA}$, respectively, which are indicative of a HS state at this temperature. These double layers are connected through CH–CH contacts between 4-*t*Bupy groups and short contacts between methyl groups from 4-*t*Bupy and C atoms from $[\text{Au}(\text{CN})_2]^-$.

The crystal structure of **3** was solved at 150 K. It crystallizes in the monoclinic *P2*₁/*c* space group. The structure is formed by $[\text{Fe}\{\text{Au}(\text{CN})_2\}]^-$ chains running along the *b* axis with a similar structure to that found in **1** but, in contrast to this last compound, the coordination site in trans to the unidentate $[\text{Au}(\text{CN})_2]^-$ ligand is occupied by a MeOH molecule and not by a terminal 4-*t*Bupy (see Fig. 3). Thus, unit cell *b* and *c* parameters of **3** are similar to those of **1** (see Table S2 in the [supplementary material](#)), while the shorter *a* parameter reflects the shorter interchain distance of **3** as a result of the replacement of one 4-*t*Bupy by MeOH. Thus, Fe(II) presents a FeN_5O octahedral coordination sphere with two N from

unidentate 4-*t*Bupy ligands, three N from $[\text{Au}(\text{CN})_2]^-$ species and one O from MeOH (see Fig. 3). As in **1**, the Au from bridging $[\text{Au}(\text{CN})_2]^-$ belonging to a chain and the terminal $[\text{Au}(\text{CN})_2]^-$ from the neighboring chain are linked through aurophilic interactions ($\text{Au}-\text{Au} = 3.126 \text{ \AA}$) leading to similar double chains. Fe–N bond lengths range from 2.113(5) to 2.231(8) $\text{\AA}$, while Fe–O bond length is 2.125(5) $\text{\AA}$, in agreement with a HS state.

C. Magnetic properties

The temperature dependence of molar magnetic susceptibility times temperature ($\chi_M T$) of **1** shows a value close to $3.8 \text{ cm}^3 \text{ K mol}^{-1}$, typical of HS state (*S* = 2), from 300 to 200 K (see Fig. 4). At lower temperatures, $\chi_M T$ presents an abrupt decrease to a value close to

FIG. 3. Structure of the chains of **3**. Fe (brown), Au (yellow), C (black), N (blue) O (red). Hydrogen atoms and one of the two possible configurations of disordered methyl groups have been omitted for clarity.

FIG. 4. Thermal dependence of $\chi_M T$ of **1**. Full circles: data recorded without irradiation; empty circles: data recorded after irradiation at 10 K.

$0 \text{ cm}^3 \text{ K mol}^{-1}$ below 140 K. This indicates a complete HS to LS conversion. A thermal hysteresis is observed with a step at 150 ($2.3 \text{ cm}^3 \text{ K mol}^{-1}$) and 175 K ($1.0 \text{ cm}^3 \text{ K mol}^{-1}$) on the cooling and heating modes, respectively, with a width (ΔT) of 30 K ($T_{1/2\uparrow} = 175 \text{ K}$ and $T_{1/2\downarrow} = 145 \text{ K}$ being $T_{1/2}$ = temperature of 50% HS to LS conversion) at a scan rate of 2 K min^{-1} . Abrupt thermal hysteretic spin transitions with steps are common in Hofmann-type compounds and are related to the presence of two crystallographically independent Fe atoms or to the presence of intermediate phases with a different space group (symmetry breaking). In contrast to this, variable-temperature single crystal x-ray diffraction studies of **1** only show one crystallographically independent Fe atom and basically the same structure at 120, 175, and 225 K in the heating mode. Thus, drastic structural changes in the step at 175 K in the heating mode were not found with respect to the structures at 120 and 225 K. In this sense, the presence of phase transitions accompanying the steps of the spin transition with tripling of the unit cell or changes in the space group explained the abrupt, hysteretic, four-step spin transition of a 3D Hofmann clathrate containing $[\text{Au}(\text{CN})_2]^-$.²⁴ In our case, we could not find a phase transition at the step temperature. This could be related to the very narrow temperature range at which it is stable. Other factor explaining these steps are the order-disorder transitions of the methyl groups of the three 4-*t*Bupy ligands as the disorder decreases in the structure at the intermediate temperature (175 K, see above). However, more detailed crystallographic and magnetic studies at other temperatures and different cooling or heating rates are needed to fully understand the SCO behavior of this compound.

The thermal hysteresis of the spin transition was confirmed by differential scanning calorimetry (DSC) (Fig. S2 in the [supplementary material](#)). Thus, an exothermic peak at 136 K upon cooling and an endothermic peak at 160 K in the heating mode were observed. The average enthalpy and entropy changes calculated from these peaks, $\Delta H = 11\text{--}14 \text{ kJ mol}^{-1}$ and $\Delta S = 64\text{--}87 \text{ J K}^{-1} \text{ mol}^{-1}$, are similar to values found in Fe(II) Hofmann-like clathrates with strong cooperative SCO behavior.²⁵

The LIESST effect was investigated by irradiation of crystals of **1** at 10 K with green light. A drastic increase of the magnetic signal was observed after irradiation reaching saturation in a very short time (less than 10 min). After this time, irradiation was switched off and the temperature was then increased at a rate of 0.3 K min^{-1} . In the 10–40 K temperature range, an increase of $\chi_M T$ to a maximum value of $3.2 \text{ cm}^3 \text{ K mol}^{-1}$ at 40 K was observed, reflecting a zero-field splitting of HS Fe(II). This value suggests an almost quantitative LS to HS photoconversion ($\sim 85\%$). At temperatures above 50 K, there is an abrupt decrease of $\chi_M T$ to reach the same values than before irradiation at 75 K. This agrees with the cooperative thermal SCO of the compound. The $T(\text{LIESST})$, defined as the minimum of the derivative of $\chi_M T$ with temperature, is 62 K. $T(\text{LIESST})$ and $T_{1/2}$ of this compound present similar values as those of 2D¹⁵ or 3D²⁶ SCO Hofmann compounds with $[\text{Au}(\text{CN})_2]^-$ reported in the literature.

IV. CONCLUSIONS

In this work, we have demonstrated that the reaction of the unidentate pyridine ligand containing a bulky *t*-butyl substituent with Fe(II) and $[\text{Au}(\text{CN})_2]^-$ affords a new type of SCO coordination polymer in the 1D compound **1**, which is formed by chains of Fe(II) complexes linked through bridging $[\text{Au}(\text{CN})_2]^-$ with three terminal 4-*t*Bupy and one monodentate $[\text{Au}(\text{CN})_2]^-$ ligand completing the octahedral coordination around Fe(II). This contrasts with the 2D networks so far obtained in similar conditions with pyridine ligands with less bulky substituents. Longer reaction times led to the 2D compound, **2**, with a coordination mode more similar to that found in the other SCO compounds based on $[\text{Au}(\text{CN})_2]^-$, and the 1D compound, **3**, in which one of the three terminal 4-*t*Bupy is replaced by a coordinating MeOH molecule. This indicates a kinetic control between several possible reaction products, which favors the compound **1** as major product. Furthermore, the similar structure of the chains found in **1** and **3** suggests that is possible to obtain this type of structure with other ligands. Optimization of the reaction conditions with 4-*t*Bupy and other pyridine ligands is in progress to prepare in a controlled way new 1D and 2D structures.

The remarkable SCO properties of the 2D compounds typically obtained with this type of ligands are also observed in the 1D compound **1**, which shows a complete and abrupt spin transition with thermal hysteresis and LIESST effect, in contrast to **2** and **3**, in which Fe(II) remains in the HS state from 120 to 300 K.²⁷ In addition to this, this novel and flexible 1D structure offers interesting possibilities to tune the spin state or adding other functionalities via host-guest chemistry or replacement of the terminal pyridine ligand, which will be explored in the near future.

SUPPLEMENTARY MATERIAL

See the [supplementary material](#) for structural tables of **1**, **2** and **3** and PXRD patterns and DSC measurements of **1**.

ACKNOWLEDGMENTS

Financial support from the EU (ERC Advanced Grant Nos. MOL-2D 788222, FET-OPEN COSMICS 766726 and COST action MOLSPIN CA15128), the Spanish MCIU (No. MAT-2017-89993-R,

and Unidad de Excelencia María de Maeztu No. CEX2019-000919-M), the Generalitat Valenciana (PROMETEO program and iDiFEDER/2018/061) and the Ministry of Education and Science of Russian Federation (Agreement No. 14.W03.31.0001) is gratefully acknowledged. We thank J. M. Martínez-Agudo and G. Agustí for magnetic measurements.

DATA AVAILABILITY

The data that support the findings of this study are available within the article and its [supplementary material](#).

REFERENCES

- ¹See for general reviews, (a) “Spin crossover in transition metal compounds,” in *Topics in Current Chemistry*, edited by P. Gülich and H. A. Goodwin (Springer Verlag, Berlin, 2004), Vols. 233–235; (b) in *Spin-Crossover Materials: Properties and Applications*, edited by M. A. Halcrow (John Wiley & Sons, Chichester, 2013)
- ²K. Senthil Kumar and M. Ruben, *Coord. Chem. Rev.* **346**, 176 (2017).
- ³G. Molnár, S. Rat, L. Salmon, W. Nicolazzi, and A. Bousseksou, *Adv. Mater.* **30**, 1703862 (2018).
- ⁴A. Enriquez-Cabrera, A. Rapakousiou, M. Piedrahita Bello, G. Molnár, L. Salmon, and A. Bousseksou, *Coord. Chem. Rev.* **419**, 213396 (2020).
- ⁵Z.-P. Ni, J.-L. Liu, M. N. Hoque, W. Liu, J.-Y. Li, Y.-C. Chen, and M.-L. Tong, *Coord. Chem. Rev.* **335**, 28 (2017).
- ⁶K. Otsubo, T. Haraguchi, and H. Kitagawa, *Coord. Chem. Rev.* **346**, 123 (2017).
- ⁷M. Meneses-Sánchez, L. Piñero-López, T. Delgado, C. Bartual-Murgui, M. C. Muñoz, P. Chakraborty, and J. A. Real, *J. Mater. Chem. C* **8**, 1623 (2020).
- ⁸M. C. Muñoz and J. A. Real, *Coord. Chem. Rev.* **255**, 2068 (2011).
- ⁹L. Piñero-López, F. J. Valverde-Muñoz, M. Seredyuk, C. Bartual-Murgui, M. C. Muñoz, and J. A. Real, *Eur. J. Inorg. Chem.* **2018**, 289 (2018).
- ¹⁰M. C. Muñoz, A. B. Gaspar, A. Galet, and J. A. Real, *Inorg. Chem.* **46**, 8182 (2007).
- ¹¹A. Galet, M. C. Muñoz, V. Martínez, and J. A. Real, *Chem. Commun.* **2004**, 2268 (2004).
- ¹²A. Galet, M. C. Muñoz, A. B. Gaspar, and J. A. Real, *Inorg. Chem.* **44**, 8749 (2005).
- ¹³T. Kosone, I. Tomori, C. Kanadani, T. Saito, T. Mochida, and T. Kitazawa, *Dalton Trans.* **39**, 1719 (2010).
- ¹⁴K. Kitase and T. Kitazawa, *Dalton Trans.* **49**, 12210 (2020).
- ¹⁵M. Seredyuk, A. B. Gaspar, V. Ksenofontov, M. Verdaguer, F. Villain, and P. Gülich, *Inorg. Chem.* **48**, 6130 (2009).
- ¹⁶G. Agustí, A. B. Gaspar, M. C. Muñoz, P. G. Lacroix, and J. A. Real, *Aust. J. Chem.* **62**, 1155 (2009).
- ¹⁷S. Yurdakul and M. Bahat, *J. Mol. Struct.* **412**, 97 (1997).
- ¹⁸G. M. Sheldrick, *Acta Crystallogr.* **A71**, 3 (2015).
- ¹⁹G. M. Sheldrick, *Acta Crystallogr.* **C71**, 3 (2015).
- ²⁰O. V. Dolomanov, L. J. Bourhis, R. J. Gildea, J. A. K. Howard, and H. Puschmann, *J. Appl. Crystallogr.* **42**, 339 (2009).
- ²¹V. García-López, M. Palacios-Corella, S. Cardona-Serra, M. Clemente-León, and E. Coronado, *Chem. Commun.* **55**, 12227 (2019).
- ²²M. Ahmed, Z. Xie, S. Thoonen, C. Hua, C. J. Kepert, J. R. Price, and S. M. Neville, *Chem. Commun.* **57**, 85 (2021).
- ²³A. Galet, M. C. Muñoz, and J. A. Real, *Chem. Commun.* **2006**, 4321 (2006).
- ²⁴J. E. Clements, J. R. Price, S. M. Neville, and C. J. Kepert, *Angew. Chem. Int. Ed.* **55**, 15105 (2016).
- ²⁵L. Piñero-López, F. J. Valverde-Muñoz, M. Seredyuk, M. C. Muñoz, M. Haukka, and J. A. Real, *Inorg. Chem.* **56**, 7038 (2017).
- ²⁶T. Delgado, M. Meneses-Sánchez, L. Piñero-López, C. Bartual-Murgui, M. C. Muñoz, and J. A. Real, *Chem. Sci.* **9**, 8446 (2018).
- ²⁷Preliminary single crystal x-ray diffraction studies of **2** and **3** from 120 to 300 K show Fe–N distances consistent with the HS state of Fe(II).