

Journal section: Operative Dentistry and Endodontics
 Publication Types: Research

doi:10.4317/jced.54552
<http://dx.doi.org/10.4317/jced.54552>

Shear bond strength of one-step self-etch adhesives to dentin: Evaluation of NaOCl pretreatment

Marco Colombo, Riccardo Beltrami, Marco Chiesa, Claudio Poggio, Andrea Scribante

Department of Clinical-Surgical, Diagnostic and Pediatric Sciences – Section of Dentistry, Policlinico “San Matteo”, Piazzale Golgi, Pavia, Italy

Correspondence:

Department of Clinical-Surgical
 Diagnostic and Pediatric Sciences – Section of Dentistry
 Policlinico “San Matteo”
 Piazzale Golgi 3, 27100 Pavia, Italy
claudio.poggio@unipv.it

Colombo M, Beltrami R, Chiesa M, Poggio C, Scribante A. Shear bond strength of one-step self-etch adhesives to dentin: Evaluation of NaOCl pretreatment. J Clin Exp Dent. 2018;10(2):e127-33.
<http://www.medicinaoral.com/odo/volumenes/v10i2/jcedv10i2p127.pdf>

Received: 30/11/2017
 Accepted: 23/12/2017

Article Number: 54552 <http://www.medicinaoral.com/odo/indice.htm>
 © Medicina Oral S. L. C.I.F. B 96689336 - eISSN: 1989-5488
 eMail: jced@jced.es
Indexed in:
 Pubmed
 Pubmed Central® (PMC)
 Scopus
 DOI® System

Abstract

Background: The aim of this study was to evaluate the influence of dentin pretreatment with NaOCl on shear bond strength of four one-step self-etch adhesives with different pH values.

Material and Methods: Bovine permanent incisors were used. Four one-step self-etch adhesives were tested: Adper™ Easy Bond, Futurabond NR, G-aenial Bond, Clearfil S3 Bond. One two-step self-etch adhesive (Clearfil SE Bond) was used as control. Group 1- no pretreatment; group 2- pretreatment with 5,25 % NaOCl; group 3- pretreatment with 37 % H₃PO₄ etching and 5,25 % NaOCl. A hybrid composite resin was inserted into the dentin surface. The specimens were tested in a universal testing machine. The examiners evaluated the fractured surfaces in optical microscope to determine failure modes, quantified with adhesive remnant index (ARI).

Results: Dentin pretreatment variably influenced bond strength values of the different adhesive systems. When no dentin pretreatment was applied, no significant differences were found ($P > .05$) among four adhesives tested. No significant differences were recorded when comparing NaOCl pretreatment with H₃PO₄ + NaOCl pretreatment for all adhesive tested ($P > .05$) except Clearfil S3 Bond that showed higher shear bond strength values when H₃PO₄ was applied. Frequencies of ARI scores were calculated.

Conclusions: The influence of dentin pretreatment with NaOCl depends on the composition of each adhesive system used. There was no difference in bond strength values among self-etch adhesives with different pH values.

Key words: Dentin, pretreatment, self-etch adhesives.

Introduction

Modern adhesive systems are classified into etch-and-rinse and self-etch adhesives (1). The techniques differ for the acid-etch step. Etch and rinse adhesive systems require acid-etching to promote dentin and enamel demineralization before monomer infiltration, while self-

etch adhesives cause a simultaneous substrate demineralization and monomer infiltration (2,3). The amount of substrate demineralization can be related to the initial pH-value of the adhesive system thus subdividing them into: mild (pH of 2 or more), moderate (pH between 1 and 2) and strong (pH of 1 or below) (1,4,5). The mo-

nomer infiltration requires a separate bonding step for two-step adhesive systems or it is combined in a single application for one-step adhesive systems (4).

In literature, various authors discussed the bond strength of self-etch adhesive systems to enamel, showing conflicting results; some studies reported comparable data to that observed with etch-and-rinse systems (6-9), whereas other studies considered them less reliable when bonding to dentin (10-12). Self-etching adhesives were introduced in order to simplify the bonding steps, thus reducing the actual bonding time. Since etching and priming of the dentin surface is done in the same step, the resin monomers penetrate the whole depth of the demineralized dentin. Incomplete resin penetration to this depth will leave an exposed demineralized dentin zone at the base of the hybrid layer. In order to increase the bond longevity for the adhesive restorations, it is very important to eliminate this demineralized dentin zone from the bond structures (13).

Pretreatment with NaOCl has nonspecific proteolytic and disinfectant properties; because of these properties, it is widely used in a variety of dental procedures, such as the treatment of root canals, caries removal, and dentin bonding techniques (14). Many studies have evaluated the effect of sodium hypochlorite treatment on the performance of different adhesive systems to dentin (15-18). It was found that sodium hypochlorite application either had no effect, or affected the performance of the different dentin adhesives (improving or reducing bonding performance) (19-21). The use of sodium hypochlorite after etching of the dentin surface was also found to remove the exposed collagen fibers that altered the dentin surface characterization (22). In fact, NaOCl applied to smear layer-covered dentin promotes the dissolution of the organic phase and the smear layer is significantly thinned (14,23). However remnants of super-oxide radicals generated by NaOCl within the dentin substrate inhibit polymerization of resin monomers thus reducing the bond-strength of adhesive systems (16).

The aim of this study was to evaluate the influence of dentin pretreatment with NaOCl on shear bond strength of four one-step self-etch adhesives with different pH values.

Material and Methods

-Specimens' preparation

One hundred and fifty bovine permanent incisors freshly extracted and stored in a solution of 0.1% (wt/vol) thymol were used as a substitute for human teeth (24,25). A criterion for tooth selection included intact buccal enamel with no cracks caused by extraction. The teeth were cleansed of soft tissue and embedded in self-curing, fast-setting acrylic resin (Rapid Repair, DeguDent GmbH, Hanau, Germany). Specially fabricated cuboidal Teflon mould were filled with the acrylic resin and

allowed to cure, thus encasing each specimen while allowing the buccal surface of dentin to be exposed. Each tooth was oriented so that its labial surface was parallel to the shearing force. The teeth were sectioned parallel to the occlusal surface to expose midcoronal dentin. The exposed dentin surfaces were wet abraded using an automated polishing machine (APL-4; Arotec S.A. Ind Com, Cotia, SP, Brazil) with a 600-grit silicon carbide abrasive paper (SiC) disks for 5 seconds, to obtain a flat and uniform dentin surface. The teeth were randomly assigned into three groups (each made of 50 specimens) according to different dentin surface pretreatments.

Group 1 - Control: no pretreatment was applied; the adhesives were applied according to the manufactures directions.

Group 2 - Pretreatment with 5,25 % NaOCl (Nielcor 5; Ognalaboratori Farmaceutici, Muggiò, Italy) application for 2 min; after rinsing and drying the specimens for 30 seconds each, the adhesives were applied according to the manufacturer's directions.

Group 3 - Pretreatment with 37% H₃PO₄ etching (Total Etch; Ivoclar Vivadent AG, Schaan, Liechtenstein) for 15 seconds and 5,25 % NaOCl (Nielcor 5; Ognalaboratori Farmaceutici, Muggiò, Italy) application for 2 min; after rinsing and drying the specimens for 30 seconds each, the adhesives were applied according to the manufacturer's directions. Each group was then divided into five subgroups of ten teeth each according the bonding agent used.

-Materials tested

The materials used in this study included four one-step self-etch adhesives with different pH values: Adper™ Easy Bond (pH=0,9), Futurabond NR (pH=1,4), G-aenial Bond (pH=1,5), Clearfil S3 Bond (pH=2,7). One two-step self-etch adhesive (Clearfil SE Bond/pH=2,1) was used as control. The specifications of all adhesive systems are listed in Table 1.

-Application of adhesive systems

The adhesive systems were applied to the demarcated bonding area. All adhesives were cured using a LED curing light in soft start-polymerization mode (Celalux 2 High-Power LED curing-light, Voco GmbH, Cuxhaven, Germany) for the times suggested by the manufacturers at a irradiance of 1000 mW/cm². After adhesive systems application, a hybrid composite resin (Grandio, Voco GmbH, Cuxhaven, Germany) was carefully inserted into the dentin surface by packing the material into cylindrical-shaped plastic matrices with an internal diameter of 2 mm and a height of 2 mm. Excess composite was carefully removed from the periphery of the matrix with an explorer. The composite was cured with an LED curing light in soft start-polymerization mode (Celalux 2 High-Power LED curing-light, Voco GmbH, Cuxhaven, Germany) for 20 seconds at a light intensity

Table 1: Adhesive systems tested.

Adhesive	Manufacturer	Batch Number	Composition	pH	Application Protocol
Adper™ Easy Bond	3M ESPE, St Paul, MN, USA	391517	HEMA, bis-GMA, Methacrylated phosphoric ester, 1,6-hexanediol dimethacrylate, methacrylate functionalized polyalkenoic, Finelt dispersed bonded silica filler, ethanol, water, initiators based on CQ, stabilizers.	0,9	1. Apply for 20s; 2. Dry with an air jet for 5s; 3. Light-cure for 10s.
Futurabond NR	VOCO, Cuxhaven, Germany	Liquid A: 045191 Liquid B: 045193	Liquid A: Methacryloyloxyalkyl acid phosphate. Liquid B: Bis-GMA, Hroxyyl methacrylate, BT, ethanol, organic acids, fluorides.	1,4	1. Mixing Liquid A and Liquid B for 5s; 2. Apply for 20s; 3. Dry with an air jet for 5s; 4. Light-cure for 10s.
G-aenial Bond	GC Corporation, Tokyo, Japan	1007061	Acetone, distilled water, dimethacrylate, 4-MET, phosphoric acid ester monomer, silicon dioxide, photo-iniziator.	1,5	1. Apply and leave for 10s. 2. Dry with an air jet for 5s. 3. Light-cure for 10s.
Clearfil ³ S Bond	Kuraray Medical, Sakazu, Okayama, Japan	0155AA	Bond: 10-MDP, Bis-GMA, HEMA, CQ, ethanol, water, colloidal silica.	2,7	1. Apply for 20s; 2. Dry with an air jet for 5s; 3. Light-cure for 10s.
Clearfil SE Bond	Kuraray Medical, Sakazu, Okayama, Japan	Primer: 1040AA Bond: 1556AA	Primer: 10-MDP, HEMA, Hydrophilic dimethacrylate, CQ, N,N-Diethanol-p-toluidine, water. Bond: 10-MDP, Bis-GMA, HEMA, Hydrophilic dimethacrylate, CQ, N,N-Diethanol-p-toluidine, silanated colloidal silica.	2,1	1. Apply Primer and leave for 20s; 2. Dry with mild air flow; 3. Apply Bond and distribute evenly with flow; 4. Light cure for 10s.

Legend: UDMA: urethane dimethacrylate; 4-MET: 4-methacryloxyethyl trimellitic acid; HEMA: 2-hydroxyethyl methacrylate; bis-GMA: bis-phenol A diglycidymethacrylate; CQ: camphoroquinone; 10-MDP: methacryloyloxydecyl dihydrogenphosphate.

of 1000 mW/cm²: the composite buildups were created. Following polymerization, specimens were stored in distilled water for 24 hours at 37°C.

-Shear bond strength testing

After storing, the specimens were tested in a universal testing machine (Model 3343, Instron Corporation, Norwood, MA, USA). Specimens were secured in the lower jaw of the machine so that the bonded cylinder base was parallel to the shear force direction. The tensile

bond strength was performed at 0.5 mm/minute until the sample rupture. Specimens were stressed in an occluso-gingival direction at a crosshead speed of 1 mm/min (26-28). The maximum load necessary to debond was recorded in Newton (N) and calculated in MPa as a ratio of Newton to surface area of the cylinder. After the testing procedure, the fractured surfaces were examined in optical microscope (Stereomicroscope SR, Zeiss, Oberkochen, Germany) at a magnification of 10X to deter-

mine failure modes and classified as adhesive failures, cohesive failures within the composite, or cohesive failures within the tooth (29). The adhesive remnant index (ARI) was used to assess the amount of adhesive left on the dentin surface (30). This scale ranges from 0 to 3. A score of 0 indicates no adhesive remaining on the tooth in the bonding area; 1 indicates less than half of the adhesive remaining on the tooth; 2 indicates more than half of the adhesive remaining on the tooth; and 3 indicates all adhesive remaining on the tooth. The ARI scores were used as a method of defining bond failure site among the dentin, the adhesive, and the composite.

-Statistical analysis

Statistical analysis was performed with Stata 9.0 software (Stata, College Station, Tx, USA). Descriptive statistics, including the mean, standard deviation, median, and minimum and maximum values were calculated

for all groups. Kolmogorov and Smirnov (KS) test was applied to assess normality of distributions. An analysis of variance (two-ways ANOVA) was applied to determine whether significant differences in debond values existed among the groups. The Dunn test was used as post-hoc. The chi-squared test was used to determine significant differences in the ARI scores among the different groups. Significance for all statistical tests was predetermined at $P<.05$.

Results

Descriptive statistics of the shear bond strength (MPa) of the different groups are illustrated in Table 2 and in Fig. 1. KS test assessed normal data distributions ($P>.05$). ANOVA showed the presence of significant differences among the various groups ($P<.001$) as reported in Table 3. Post hoc Dunn test showed that when no dentin pre-




Fig. 1: Mean shear bond strength and standard deviations of the different groups.

Table 2: Descriptive statistics (in MPa) of shear bond strengths of the 10 subgroups tested (each subgroup consisted of 10 specimens). SD: Standard deviation.

Adhesive	Pretreatment	Mean	SD	Min	Mdn	Max
Adper™ Easy Bond	No pretreatment	16,55	5,47	10,98	15,47	25,28
Futurabond NR	No pretreatment	16,13	6,06	10,35	13,71	26,39
G-aenial Bond	No pretreatment	15,96	3,58	10,90	15,29	20,10
Clearfil S ³ Bond	No pretreatment	11,55	3,80	6,77	10,62	17,59
Clearfil SE Bond	No pretreatment	15,65	2,71	12,64	15,17	20,26
Adper™ Easy Bond	NaOCl	13,06	3,15	8,57	14,22	16,24
Futurabond NR	NaOCl	14,43	3,09	11,20	13,59	18,68
G-aenial Bond	NaOCl	10,62	4,08	5,77	10,17	16,32
Clearfil S ³ Bond	NaOCl	12,88	1,53	11,33	12,14	14,72
Clearfil SE Bond	NaOCl	18,06	4,19	13,85	18,09	25,37
Adper™ Easy Bond	H3PO4 + NaOCl	16,04	2,12	12,85	17,03	17,74
Futurabond NR	H3PO4 + NaOCl	15,22	3,29	12,74	14,05	20,06
G-aenial Bond	H3PO4 + NaOCl	8,48	3,00	5,48	7,79	12,97
Clearfil S ³ Bond	H3PO4 + NaOCl	17,14	5,40	12,77	14,25	24,48
Clearfil SE Bond	H3PO4 + NaOCl	16,15	6,64	8,54	13,87	23,45

treatment was applied, no significant differences were found ($P>.05$) among four different adhesives tested (Adper™ Easy bond, Futurabond NR, G-aenial Bond and Clearfil SE Bond) and that all showed significantly higher shear bond strength values than Clearfil S3 Bond ($P<.01$). Moreover, when NaOCl pretreatment was conducted four adhesives tested (Adper™ Easy bond, Futurabond NR, Clearfil S3 Bond and Clearfil SE Bond) showed no significant differences in shear bond strength values when compared with untreated groups ($P>.05$), whereas when testing G-aenial Bond strength values were significantly lower than those recorded under untreated dentin ($P<.001$). Correspondingly, when H3PO4 + NaOCl pretreatment was tested three adhesives (Adper™ Easy

bond, Futurabond NR and Clearfil SE Bond) showed no significant differences in shear bond strength values when compared with untreated groups ($P>.05$), whereas when testing G-aenial Bond strength values were significantly lower than those recorded under untreated dentin ($P<.001$) while Clearfil S3 Bond showed significantly higher values ($P>.05$). Finally, no significant differences were recorded when comparing NaOCl pretreatment with H₃PO₄ + NaOCl pretreatment for all adhesive tested ($P>.05$) except Clearfil S3 Bond. When comparing ARI Score results of the different groups no statistical difference was found in frequency distribution among various groups, that all showed a significant prevalence of ARI Score of “0” and “1”, as illustrated in Fig. 2.

Table 3: Mean and standard deviation (in parenthesis) in MPa for each material tested. The same superscript letter in vertical row indicate no significant differences ($P>0.05$).

Adhesives	Dentin Pretreatment		
	No Pretreat.	NaOCl	H ₃ PO ₄ +NaOCl
Adper™ Easy Bond	16.55 (2.74) ^a	13.06 (2.25) ^a	16.04 (2.12) ^a
Futurabond NR	16.13 (3.03) ^a	14.43 (1.54) ^a	15.22 (1.65) ^a
G-aenial Bond	15.96 (1.79) ^a	10.62 (2.04) ^c	8.48 (1.50) ^c
Clearfil ³ S Bond	11.55 (1.90) ^b	12.88 (0.77) ^b	17.14 (2.70) ^d
Clearfil SE Bond	15.65 (1.35) ^a	18.06 (2.10) ^a	16.15 (3.32) ^a




Fig. 2: Distribution of ARI scores of the different groups.

Discussion

In order to compare data from the current study with that reported in previous bovine dentin bond strength tests, bovine teeth were used as a substitute for human teeth in the current study. Bovine teeth have large, flat surfaces and are unlikely to have undergone prior caries challenges that could affect the test result. The mineral distribution within the carious lesions in bovine teeth is reported to be similar to human teeth, and the structural changes that occur in human and bovine teeth are also similar (31,32). Modern one-step self-etch adhesives simplify the technique and reduce the number of clinical steps but substrate pretreatment could influence their bond strength values (33-35). The effect of such additional pretreatment on dentin bond strength is also controversially discussed in the literature. Its use might be beneficial with some self-etching adhesives, but this depends largely on the properties of the adhesive itself. Differently from other studies, the present research focused on normal dentin because in the clinical practice there is no need to leave caries-affected dentin. Moreover it has been demonstrated a significantly lower shear bond strength in caries-affected dentin than in normal dentin using one-step and two-step self-etching adhesives (36); in fact the acid-resistant minerals within the caries-affected dentin smear layer, which are derived from the occluding mineral deposits within the dentinal tubules, might interfere with dissolution of the smear layer by the self-etch adhesives (37).

As reported in Fig. 1, Adper™ Easy Bond, Futura-bond NR, Clearfil S3 Bond and the control Clearfil SE Bond maintained shear bond strength constant both after pretreatment with 5,25 % NaOCl application for 2 min, both after pretreatment with 37% H₃PO₄ etching for 15 seconds and 5,25 % NaOCl for 2 min. Differently, G-aenial Bond showed statistical significant reduction of shear bond strength after pretreatment. These results are in contrast with the current concepts on resin/dentin adhesion which suggest that bonding to dentin prior to use of self-etching primers would be more predictably achieved by first removing the smear layer with a separate proteolytic conditioning step (38). The lower shear bond strength obtained by G-aenial Bond evaluated after NaOCl treatment may have been caused by the association of presence of an additional demineralization induced by the self-etching functional monomers, occurrence of residual glycosaminoglycans components of the organic matrix (which are resistant to strong acids and NaOCl) and disruption by NaOCl of pyridinoline cross-links that occur in the Type I dentin collagen, with the formation of chloramines and protein derived radical intermediates (39).

Reactive radicals could interfere with vinyl free-radicals emitted during photo-polymerization thus reducing the conversion from monomer to polymer (39). For the rem-

nant adhesives tested the application of pretreatments did not influence the shear bond strength even if it contributed with non-specific proteolytic properties in the reduction of the smear layer due to the dissolution of the organic phase. Clearfil S3 Bond showed a significant increase in shear bond strength as reported in Table 3. As manufacturers suggested, this adhesive system presents a Molecular Dispersion Technology, which enables the two-phase liquids of hydrophilic and hydrophobic components to be maintained in a homogeneous state even when the solvent is evaporated, improving bond quality. This aspect is well confirmed by the results of the ARI scores; as showed in Fig. 2, the failure of the adhesion when pretreatment is applied to Clearfil S3 Bond is significantly higher among the adhesive. When shear bond strength is reported to be significantly lower, as for G-aenial Bond, the ARI score when pretreatment is applied indicates in all cases not a cohesive failure, but a failure of the adhesion at the interface between dentin and the adhesive system (40).

Conclusions

The pretreatment with H₃PO₄ and NaOCl enhanced the shear bond strength of Adper™ Easy Bond, Futura-bond NR, Clearfil S3 Bond and Clearfil SE Bond; but the differences between the values were not statistically significant. Differently, the pretreatment reduced significantly the shear bond strength of G-aenial Bond. Self-etch adhesives failed primarily in the adhesive substrate (ARI = 0 and ARI=1), without significantly differences among the various groups.

References

1. Van Meerbeek B, De Munck J, Yoshida Y, Inoue S, Vargas M, Vijay P, et al. Adhesion to enamel and dentin: current status and future challenges. *Oper Dent.* 2003;28:215-35.
2. Sano H, Shono T, Takatsu T, Hosoda H. Microporous dentin zone beneath resin impregnated layer. *Oper Dent.* 1994;19:59-64.
3. Carvalho RM, Chersoni S, Frankenberger R, Pashley DH, Prati C, Tay FR. A challenge to the conventional wisdom that simultaneous etching and resin infiltration always occurs in self-etch adhesives. *Biomaterials.* 2005;26:1035-42.
4. Nikaido T, Nakajima M, Higashi T, Kanemura N, Pereira PN, Tagami J. Shear bond strengths of a single-step bonding system to enamel and dentin. *Dent Mat J.* 1997;16:40-7.
5. Lühns A-K, Guhr S, Schilke R, Borchers L, Geurtsen W, Gunay H. Shear bond strength of self-etch adhesives to enamel with additional phosphoric acid etching. *Oper Dent.* 2008;33:155-62.
6. Ibarra G, Vargas MA, Armstrong SR, Cobbb DS. Microtensile bond strength of selfetching adhesives to ground and unground enamel. *J Adhes Dent.* 2002;4:115-24.
7. Kiremitçi A, Yalçın F, Gökalp S. Bonding to enamel and dentin using self-etching adhesive systems. *Quintessence Int.* 2004;35:367-70.
8. Pilecki P, Stone DG, Sherriff M, Watson TF. Microtensile bond strengths to enamel of self-etching and one bottle adhesive systems. *J Oral Rehab.* 2005;32:531-40.
9. Walter R, Swift JE, Boushell LW. Enamel and dentin bond strength of a new self-etch adhesive system. *J Esthet Restor Dent.* 2011;23:390-6.

10. De Munck J, Van Meerbeek B, Satoshi I, Vargas M, Yoshida Y, Armstrong S, et al. Microtensile bond strengths of one- and two-step self-etch adhesives to bur-cut enamel and dentin. *Am J Dent.* 2003;16:414-20.
11. Perdigão J, Gomes G, Duarte S Jr, Lopes MM. Enamel bond strengths of pairs of adhesives from the same manufacturer. *Oper Dent.* 2005;30:492-9.
12. Brackett WW, Ito S, Nishitani Y, Haisch LD, Pashley DH. The microtensile bond strength of self-etching adhesives to ground enamel. *Oper Dent.* 2006;31:332-7.
13. Hashimoto M, Ohno H, Kaga M, Endo K, Sano H, Oguchi H. In vivo degradation of resin-dentin bonds in humans over 1 to 3 years. *J Dental Res.* 2000;79:1385-91.
14. Sakae T, Mishima H, Kozawa Y, Endo K, Sano H, Oguchi H. Changes in bovine dentin mineral with sodium hypochlorite treatment. *J Dent Res.* 1988;67:1229-34.
15. Saboia P, Rodrigues A, Pimenta L. 2-year clinical evaluation of sodium hypochlorite treatment in restoration of non carious cervical lesions: A pilot study. *Oper Dent.* 2006;31:530-5.
16. Santos J, Carrilho M, De Goes M, Zaia AA, Gomes BP, Souza-Filho FJ, et al. Effect of chemical irrigants on the bond strength of a self-etching adhesive to pulp chamber dentin. *J Endod.* 2006;32:1088-90.
17. Vargas MA, Cobb DS, Armstrong SR. Resin-dentin shear bond strength and interfacial ultrastructure with and without a hybrid layer. *Oper Dent.* 1997;22:159-66.
18. Vongphan N, Senawongse P, Somsiri W, Hamirattisai C. Effects of sodium ascorbate on microtensile bond strength of total-etching adhesive system to NaOCl treated dentine. *J Dent.* 2005;33:689-95.
19. Celik C, Erkut S, Gulsahi K, Yamanel K, Kucukesmen C. Effect of sodium ascorbate on bond strength of different adhesive systems to NaOCl-treated dentin. *Aust Endod J.* 2010;36:12-8.
20. Stevens CD. Immediate Shear Bond Strength of Resin Cements to Sodium Hypochlorite-treated Dentin. *J Endod.* 2014;40:1459-62.
21. Potter JV, Zhu CF, McAlister T, Jones JD. Effects of pretreating preparations with sodium hypochlorite on bonding composite resin restorations. *Gen Dent.* 2013;61:e23-5.
22. Correr G, Alonso R, Grando M, Borges AF, Puppini-Rontani RM. Effect of sodium hypochlorite on primary dentin-A scanning electron microscopy (SEM) evaluation. *J Dent.* 2006;34:454-9.
23. Mountouris G, Silikas N, Eliades G. Effect of sodium hypochlorite treatment on the molecular composition and morphology of human coronal dentin. *J Adhes Dent.* 2004;6:175-82.
24. Montes MA, De Goes MF, Sinhorette MA. The in vitro morphological effects of some current pre-treatments on dentin surface: a SEM evaluation. *Oper Dent.* 2005;30:201-12.
25. Nikaido T, Takano Y, Sasafuchi Y, Burrow MF, Tagami J. Bond strengths to endodontically treated teeth. *Am J Dent.* 1999;12:177-80.
26. Jobalia SB, Valente RM, de Rijk WG, BeGole EA, Evans CA. Bond strength of visible light-cured glass ionomer orthodontic cement. *Am J Orthod Dentofacial Orthop.* 1997;112:205-8.
27. Millett DT, Cattanaach D, McFadzean R, Pattinson J, McColl J. Laboratory evaluation of a compomer and a resin-modified glass ionomer cement for orthodontic bonding. *Angle Orthodontist.* 1999;69:58-63.
28. Cacciafesta V, Sfondrini MF, De Angelis M, Scribante A, Klersy C. Effect of water and saliva contamination on shear bond strength of brackets bonded with conventional, hydrophilic, and self-etching primers. *Am J Orthod Dentofacial Orthop.* 2003;123:633-40.
29. Mirzakouchaki B, Kimyai S, Hydari M, Shahrbaaf S, Mirzakouchaki-Boroujeni P. Effect of self-etching primer/adhesive and conventional bonding on the shear bond strength in metallic and ceramic brackets. *Med Oral Patol Oral Cir Bucal.* 2012;17:e164-70.
30. Årtun J, Bergland S. Clinical trials with crystal growth conditioning as an alternative to acid-etch enamel pretreatment. *Am J Orthod.* 1984;85:333-40.
31. Edmunds DH, Whittaker DK, Green RM. Suitability of human, bovine, equine, and ovine tooth enamel for studies of artificial bacterial carious lesions. *Caries Research.* 1988;22:327-36.
32. Tsuchiya H, Tsubota K, Iwasa M, Ando S, Miyazaki M, Platt JA. Influence of adhesive application time on enamel bond strength of single-step self-etch adhesive systems. *Oper Dent.* 2010;35:77-83.
33. Van Meerbeek B, Van Landuyt K, De Munck J, Hashimoto M, Peumans M, Lambrechts P, et al. Technique-sensitivity of contemporary adhesives. *Dent Mat J.* 2005;24:1-13.
34. Hiraishi N, Breschi L, Prati C, Ferrari M, Tagami J, King NM. Technique sensitivity associated with air-drying of HEMA-free, single-bottle, one-step self-etch adhesives. *Dent Mat.* 2007;23:498-505.
35. Dias WRL, Pereira PNR, Swift EJ. Effect of surface preparation on microtensile bond strength of three adhesive systems to bovine enamel. *J Adhes Dent.* 2004;6:279-85.
36. Taniguchi G, Nakajima M, Hosaka K, Iwamoto N, Ikeda M, Foxton RM, Tagami J. Improving the effect of NaOCl pretreatment on bonding to caries-affected dentin using self-etch adhesives. *J Dent.* 2009;37:769-75.
37. Kunawarote S, Nakajima M, Foxton RM, Tagami J. Effect of pretreatment with mildly acidic hypochlorous acid on adhesion to caries-affected dentin using a self-etch adhesive. *Eur J Oral Sci.* 2011;119:86-92.
38. Toledano M, Perdigão J, Osorio E, Osorio R. Influence of NaOCl deproteinization on shear bond strength in function of dentin depth. *Am J Dent.* 2002;15:252-5.
39. Erhardt MC, Osorio E, Aguilera FS, Proença JP, Osorio R, Toledano M. Influence of dentin acid-etching and NaOCl-treatment on bond strengths of self-etch adhesives. *Am J Dent.* 2008;21:44-8.
40. Charles A, Senkutvan R, Ramya RS, Jacob S. Evaluation of shear bond strength with different enamel pretreatments: an in vitro study. *Indian J Dent Res.* 2014;25:470-4.

Conflicts of Interest

The authors have declared that no conflict of interest exist.